

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C01B 31/00, C07F 15/04, 15/00	A1	(11) International Publication Number: WO 95/10481 (43) International Publication Date: 20 April 1995 (20.04.95)
(21) International Application Number: PCT/US94/11043 (22) International Filing Date: 6 October 1994 (06.10.94) (30) Priority Data: 08/135,702 13 October 1993 (13.10.93) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventor: FAGAN, Paul, Joseph; 10 Tenby Drive, Wilmington, DE 19803-2619 (US). (74) Agents: BIRCH, Linda, D. et al.; E.I. Du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: CARBON NANOTUBES AND NESTED FULLERENES SUPPORTING TRANSITION METALS (57) Abstract This invention provides a composition, comprising a carbon nanotube and/or a nested fullerene having transition metal particles, clusters, and/or coatings supported thereon; and a method for their preparation; the metal is preferably from the group Cr, Mo, W, Mn, Re, Fe, Ru, Os, Co, Rh, Ir, Ni, Pd, Pt, Cu, Ag and Au.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

TITLECARBON NANOTUBES AND NESTED
FULLERENES SUPPORTING TRANSITION METALSField of the Invention

5 This invention relates to hollow, graphitic tubules
of carbon of nanometer dimensions, called nanotubes, and
nested fullerenes. Specifically, this invention relates
to compositions comprising these nanotubes and nested
fullerenes having metals supported thereon, and a method
10 for their preparation.

Background of the Invention

The C₆₀ molecule was originally discovered as a
peak in the mass spectra of quenched carbon vapor. To
explain the stability of this molecule, Kroto et al.,
15 "C₆₀: Buckminsterfullerene", *Nature*, 318 (1985) 162-163,
first proposed the structure of a truncated icosahedron,
a polygon with 60 vertices and 32 faces, 12 of which are
pentagonal and 20 hexagonal, commonly encountered as a
soccer ball, and dubbed Buckminsterfullerene, or
20 fullerene. Fullerenes may be defined by the following
formula: C_n, wherein $n \geq 60$.

Kratschmer et al., "Solid C₆₀ a new form of
carbon", *Nature*, 347 (1990) 354-358, pioneered the
electric arc method for generating fullerenes, which has
25 since become the standard technique.

A simple modification of this technique, increasing
the buffer gas, helium, pressure from 100 torr
(13,332 Pa) to 500 torr (66,661 Pa), resulted in the
formation of carbon nanotubes, as reported by Ajayan et
30 al. in "Large-scale synthesis of carbon nanotubes",
Nature, 358 (1992) 220-222. The carbon nanotubes
consist of nested concentric tubes of carbon where each
tube is made up of curved graphite-like sheets of
carbon. The tubes are hollow on the inside and the ends
35 of the tube are usually sealed with fullerene-like caps.

The tubes have a high aspect ratio with the diameter being in the range from 2 nanometers to several tens of nanometers and the length being as long as several microns. Also produced are concentric hollow polygons, commonly called nested fullerenes.

As reported by Daniel Ugarte in *Nature*, 359, (1992) 708-709, irradiation with an electron beam can convert nanotubes to concentric hollow spheres.

It has been found possible to open carbon nanotubes with chemical methods as reported by Tsang et al., "Thinning and opening of carbon nanotubes by oxidation using carbon dioxide", *Nature*, 362 (1993) 520-522. Tsang et al. opened the tubes by heating them in carbon dioxide at 850°C. Ajayan et al. opened the tubes by heating the tubes in air above about 700°C, as reported in *Nature*, 362 (1993) 522-525.

Two reports suggest lead and lanthanum carbide can be placed inside carbon nanotubes (Ajayan et al., *Nature* (London), 1993, vol. 361, 333-334; Ruoff et al., *Science*, 1993, vol. 259, 346-8). During the process of Ajayan et al., lead particles were deposited onto nanotubes following electron beam evaporation of pure lead under vacuum. After annealing in an oven at approximately 400°C, the melting point of lead, the lead particles that had been deposited on closed caps of the tubes appeared to melt and enter the tubes.

An object of the present invention is to provide sealed and unsealed carbon nanotubes and nested fullerenes with supported transition metal particles, clusters of particles, coatings, or a combination thereof attached to the outside surface of the nanotubes and nested fullerenes.

SUMMARY OF THE INVENTION

This invention provides a composition comprising at least one from the group consisting of a carbon nanotube

and a nested fullerene, having at least one transition metal supported thereon, said transition metal being selected from the group consisting of: Sc, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Y, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt and Au.

This invention also provides a process for the preparation of a composition comprising at least one from the group consisting of a carbon nanotube and a nested fullerene, having at least one transition metal supported thereon, comprising the steps of: reacting at least one of the group consisting of a carbon nanotube and a nested fullerene with at least one metal-complex of the formula L_nM , wherein L = a metal ligand; n is an integer from 1 to 8; and M is a transition metal selected from the group consisting of Sc, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Y, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt and Au, by slurring with an inert solvent; isolating the reaction product; and washing the reaction product to remove excess metal complex. In addition the reaction product may be heated under vacuum to a temperature from ambient to about 1000°C, driving off any residual metal-complex from the carbon nanotubes and nested fullerenes with metal particles, clusters, and/or coatings attached thereto.

This invention further provides a composition comprising at least one from the group consisting of a carbon nanotube and a nested fullerene, having at least one transition metal supported thereon, made by a process comprising the steps of: reacting at least one of the group consisting of a carbon nanotube and a nested fullerene with at least one metal-complex of the formula L_nM , wherein L = a metal ligand; n is an integer from 1 to 8; and M is a transition metal selected from the group consisting of Sc, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Y, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os,

Ir, Pt and Au, by slurring with an inert solvent;
isolating the reaction product; and washing the reaction
product to remove excess metal-complex. In addition the
reaction product may be heated under vacuum to a
5 temperature from ambient to about 1000°C.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying photomicrographs, which are
incorporated in and constitute a part of the
specification, illustrate the presently preferred
10 embodiments of the invention and, together with the
general description given above and the detailed
description of the preferred embodiments given below,
serve to explain the principles of the invention.

FIG. 1A is a photomicrograph of a nanotube with
15 platinum particles, clusters of particles, and a coating
supported thereon according to the present invention
prior to heat treatment (Example 1).

FIG. 1B is a photomicrograph of nanotubes with
platinum particles, clusters of particles, and a coating
20 supported thereon according to the present invention
after heat treatment (Example 1).

FIG. 2A is a photomicrograph of a nanotube with
palladium particles, clusters, and coating supported
thereon according to the present invention prior to heat
25 treatment (Example 2).

FIG. 2B is a photomicrograph of a nanotube with
palladium particles, clusters, and coating supported
thereon according to the present invention after heat
treatment (Example 2).

30 FIG. 3A is a photomicrograph of a nanotube with
nickel particles, clusters and coating supported thereon
according to the present invention prior to heat
treatment (Example 3).

FIG. 3B is a photomicrograph of a nanotube with
35 nickel particles, clusters and coating supported thereon

according to the present invention after heat treatment (Example 3).

DETAILED DESCRIPTION OF THE INVENTION

This invention provides a composition comprising at least one from the group consisting of a carbon nanotube and a nested fullerene, having at least one transition metal supported thereon, said transition metal being selected from the group consisting of: Sc, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Y, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt and Au.

For the purpose of the present invention, a carbon nanotube comprises a series of hollow, coaxial tubes, wherein each tube is made up of curved graphite-like sheets of carbon of nanometer dimensions. The nanotubes are hollow on the inside and the ends of the nanotube are usually sealed with fullerene-like caps. The dimensions of the nanotube are about 0.1 to 200 nm in diameter and about 1 to 100 microns in length.

The carbon nanotube of the present invention can be prepared by the procedure of Ajayan et al., in "Large-scale synthesis of carbon nanotubes", *Nature*, 358 (1992) 220-222, incorporated by reference herein.

The composition of the present invention may comprise nanotubes with sealed or unsealed ends. The ends may be unsealed with chemical methods as reported by Tsang et al., "Thinning and opening of carbon nanotubes by oxidation using carbon dioxide", *Nature*, 362 (1993) 520-522, wherein the tubes were opened by heating them in carbon dioxide at 850°C. Ajayan et al. opened the tubes by heating them in air above about 700°C, as reported in *Nature*, 362 (1993) 522-525.

A nested fullerene of the present invention comprises a series of hollow, concentric spheres or polyhedra of carbon. Nested fullerenes can be prepared

by irradiating a carbon nanotube with an electron beam as reported by Ugarte, *Nature*, 359 (1992) 708-709.

A transition metal is supported by the carbon nanotube and/or nested fullerene of the present invention. For the purpose of the present invention the transition metal is selected from the group consisting of Sc, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Y, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt and Au. Preferably the transition metal is selected from the group consisting of: Cr, Mo, W, Mn, Re, Fe, Ru, Os, Co, Rh, Ir, Ni, Pd, Pt, Cu, Ag and Au; more preferably, Co, Rh, Ir, Ni, Pd and Pt; most preferably, Ni, Pd and Pt. At least one transition metal is supported on the nanotube and/or nested fullerene. As shown in Fig. 1, Fig. 2 and Fig. 3, the transition metal may be in the form of individual metal particles, clusters of metal particles, a coating, or a combination thereof. The particles and clusters range in size from about 0.8 to 20 nm in size, and the coatings are generally less than about 30 Å thick.

Since the chemistry of the outer surface of carbon nanotubes and nested fullerenes is not fully known, for the purpose of the present invention the term "supported" shall mean that the transition metal is attached to the outside surface of the nanotube and/or nested fullerene with the transition metal in the form of particles, clusters of particles, and/or a coating. Since the carbon nanotubes and nested fullerenes have curved carbon surfaces, deposition of metals on these materials results in a unique form of metal on carbon.

This invention also provides a process for the preparation of a composition comprising at least one from the group consisting of a carbon nanotube and a nested fullerene, having at least one transition metal supported thereon, said transition metal from the group

- consisting of Sc, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Y, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt and Au. The process comprises reacting at least one of the group consisting of a carbon nanotube and a nested
- 5 fullerene (as defined above) with at least one metal-complex of the formula L_nM , wherein L = a metal ligand; n is an integer from 1 to 8; and M is a transition metal selected from the group consisting of Sc, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Y, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Hf, Ta,
- 10 W, Re, Os, Ir, Pt and Au. Preferably, the transition metal is Cr, Mo, W, Mn, Re, Fe, Ru, Os, Co, Rh, Ir, Ni, Pd, Pt, Cu, Ag and Au; more preferably, Co, Rh, Ir, Ni, Pd and Pt; and most preferably, Ni, Pd and Pt. The reaction takes place by slurring the carbon nanotube
- 15 and/or nested fullerene with the metal-complex in an inert solvent. Suitable inert solvents are unreactive towards the metal complex. Non-polar hydrocarbons such as alkanes, e.g., hexane, and aromatics, e.g., benzene and toluene, are preferred. Suitable metal ligands are
- 20 characterized by being labile, that is they are removed upon heating. Examples of organics that are volatile in the temperature range of 25°C to 500°C suitable as a metal ligand are ethylene, ammonia, cyclopentadienyl, cyclooctadiene (C_8H_{16}) and triethylphosphine ($(C_2H_5)_3P$).
- 25 Cyclooctadiene and triethylphosphine are preferred.

The material is isolated by filtering, centrifuging or decanting and washed with an inert solvent, as described above, to remove excess metal-complex.

- Examination by high resolution transmission
- 30 electron microscopy at this stage in the process shows a material with an amorphous coating of the metal and some remaining ligands. Heating this material in vacuo from ambient to about 1000°C, preferably, about 300°C to 400°C drives off any residual metal-complex ligand,
- 35 producing the carbon nanotube and/or nested fullerene

with metal particles, clusters of particles and/or coatings attached. The resulting particles and clusters range from about 0.8 to 20 nm in size, and the coatings are generally less than about 30 Å thick.

- 5 This invention further provides a composition comprising at least one from the group consisting of a carbon nanotube and a nested fullerene, having at least one transition metal supported thereon, made by a process comprising the steps of: reacting at least one
10 of the group consisting of a carbon nanotube and a nested fullerene with at least one metal-complex of the formula L_nM , wherein L = a metal ligand; n is an integer from 1 to 8; and M is a transition metal selected from the group consisting of Sc, Ti, V, Cr, Mn, Fe, Co, Ni,
15 Cu, Y, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt and Au; preferably, Cr, Mo, W, Mn, Re, Fe, Ru, Os, Co, Rh, Ir, Ni, Pd, Pt, Cu, Ag and Au; more preferably, Co, Rh, Ir, Ni, Pd and Pt; and most preferably, Ni, Pd and Pt, by slurring with an inert
20 solvent. Suitable inert solvents are unreactive towards the metal complex. Non-polar hydrocarbons such as alkanes, e.g., hexane, and aromatics, e.g., benzene and toluene, are preferred. After isolating the reaction product by filtering, centrifuging or decanting, the
25 reaction product is washed with an inert solvent, as described above, to remove excess metal-complex. In addition the reaction product may be heated under vacuum to a temperature from ambient to about 1000°C, preferably about 300°C to 400°C, to form the transition
30 metal supported composition.

General metal on carbon catalysts are used in many industrial applications and activity is found to be extremely structure dependent. Metal supported on various forms of amorphous carbon, which largely contain
35 flat, graphitic sheets of carbon are well known

catalysts. Palladium supported on the surface of carbon particles is particularly useful; for a review, see *Palladium: Recovery, Properties and Uses*, E. M. Wise, Academic Press, New York, 1968. The novel metal and carbon compositions of the present invention in which metal is supported on a curved surface are useful as catalysts in chemical reactions such as hydrogenation of organic substrates, for example, hydrogenation of diphenylacetylene to cis-stilbene and trans-stilbene. Other uses for compositions of the present invention comprise catalyzing reactions, such as dehydrohalogenation, hydrocarbon cracking, and dehydrogenation; fragmentation reactions, such as decarbonylation and decarboxamidation; and isomerization reactions.

The details of the invention at hand can be further understood by reference to the following examples.

EXAMPLE 1

A mixture of carbon nanotubes and nested fullerenes, purchased from Terra Simco Company, Martinsburg, WV, 0.100 g, were placed in a flask with 5-8 ml of hexane. To this was added 0.100 g of $[(C_2H_5)_3P]_4Pt$. This was stirred for 18 hours. The resulting black solid was then isolated by filtration, and washed several times with hexane to remove excess starting material. Examination of a small sample of this material by high resolution transmission electron microscopy revealed the carbon nanotubes are coated with a thin layer of metal-containing amorphous material as shown in Fig. 1A. The solid was dried in vacuo, and then heated to 300°C to 400°C under high vacuum. Examination of the resulting material by high resolution electron microscopy revealed it is made up of carbon nanotubes and nested fullerenes having 10-80 Å platinum clusters attached to the outer surface in some regions,

along with regions coated with a layer or layers of platinum metal as shown in Fig. 1B.

EXAMPLE 2

A mixture of carbon nanotubes and nested
5 fullerenes, purchased from Terra Simco Company,
Martinsburg, WV, 0.100 g, were placed in a flask with
5-8 ml of hexane. To this was added 0.100 g of
[(C₂H₅)₃P]₄Pd. This was stirred for 18 hours. The
resulting black solid was then isolated by filtration,
10 and washed several times with hexane to remove excess
starting material. Examination of a small sample of
this material by high resolution transmission electron
microscopy revealed the carbon nanotubes are coated with
a thin layer of metal-containing amorphous material.
15 The solid was dried in vacuo, and then heated to 300°C
to 400°C under high vacuum. Examination of the
resulting material by high resolution electron
microscopy revealed it is made up of carbon nanotubes
and nested fullerenes having 10-80 Å palladium clusters
20 attached to the outer surface in some regions, along
with regions coated with a layer or layers of palladium
metal.

EXAMPLE 3

A mixture of carbon nanotubes and nested
25 fullerenes, purchased from Terra Simco Company,
Martinsburg, WV, 0.100 g, were placed in a flask with
5-8 ml of hexane. To this was added 0.100 g of
[(C₂H₅)₃P]₄Ni. This was stirred for 18 hours. The
resulting black solid was then isolated by filtration,
30 and washed several times with hexane to remove excess
starting material. Examination of a small sample of
this material by high resolution transmission electron
microscopy revealed the carbon nanotubes are coated with
a thin layer of metal-containing amorphous material as
35 shown in Fig. 1A. The solid was dried in vacuo, and

then heated to 300°C to 400°C under high vacuum. Examination of the resulting material by high resolution electron microscopy revealed it is made up of carbon nanotubes having nickel coatings attached to the outer surface in some regions having thicknesses of about 10 to 30 Å.

EXAMPLE 4

A Fisher-Porter bottle was charged with 0.200 g of a mixture of carbon nanotubes and nested fullerenes, purchased commercially from Terra Simco Company, Martinsburg, WV, with palladium supported thereon, heat treated at 400°C in high vacuum, and having approximately 0.5 to 0.8 weight percent palladium, 0.500 g of diphenylacetylene, and 5 mL of toluene. The bottle was attached to a pressure head, and the apparatus was pressurized to 60 psi (4.1×10^5 Pa) of hydrogen gas. The reaction was stirred and heated in an 150°C oil bath for one week. The pressure was released, and the reaction cooled. The toluene solution was filtered from the carbon nanotubes, and was removed in vacuo. Analysis of the product (0.5 g) by ^1H NMR revealed a 10% conversion of the diphenylacetylene to cis- and trans-stilbene. The ratio of cis- to trans-stilbene was 80:20. In a control experiment, no hydrogenation was observed in the absence of palladium supported nanotubes, or with carbon nanotubes without supported Pd, under the same conditions.

WHAT IS CLAIMED IS:

1. A composition, comprising: at least one from the group consisting of a carbon nanotube and a nested fullerene, having at least one transition metal supported thereon, said transition metal being selected from the group consisting of: Sc, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Y, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt and Au.
2. A composition as recited in Claim 1, wherein said transition metal is supported upon said carbon nanotube.
3. A composition as recited in Claim 1, wherein said metal is supported upon said nested fullerene.
4. A composition as recited in Claim 1, wherein said transition metal is selected from the group consisting of: Cr, Mo, W, Mn, Re, Fe, Ru, Os, Co, Rh, Ir, Ni, Pd, Pt, Cu, Ag and Au.
5. A composition as recited in Claim 4, wherein said transition metal is selected from the group consisting of: Ni, Pd and Pt.
6. A process for the preparation of a composition comprising at least one from the group consisting of a carbon nanotube and a nested fullerene, having at least one transition metal supported thereon, comprising the steps of:
 - (a) reacting at least one of the group consisting of a carbon nanotube and a nested fullerene with at least one metal complex of the formula L_nM , wherein L = a metal ligand; n is an integer from 1 to 8; and M is a transition metal selected from the group consisting of Sc, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Y, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt and Au by slurring in an inert solvent;
 - (b) isolating the reaction product; and

(c) washing the reaction product to remove excess metal complex.

7. The process of Claim 6, wherein the complex is $[(C_2H_5)_3P]_4M$ and M is selected from the group consisting of Ni, Pd and Pt.

8. The process of Claim 5, wherein M is selected from the group consisting of Cr, Mo, W, Mn, Re, Fe, Ru, Os, Co, Rh, Ir, Ni, Pd, Pt, Cu, Ag and Au.

9. The process of Claim 8, wherein the metal is selected from the group consisting of Ni, Pd and Pt.

10. The process of Claim 6, further comprising the step of:

(a) heating the reaction product under vacuum to a temperature from ambient to about 1000°C.

11. The process of Claim 10, wherein the temperature is from about 300°C to about 400°C.

12. A composition comprising at least one from the group consisting of a carbon nanotube and a nested fullerene, having at least one transition metal supported thereon, made by a process comprising the steps of:

(a) reacting at least one of the group consisting of a carbon nanotube and a nested fullerene with at least one metal complex of the formula L_nM , wherein L = a metal ligand; n is an integer from 1 to 8; and M is a transition metal selected from the group consisting of Sc, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Y, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt and Au by slurring with an inert solvent;

(b) isolating the reaction product; and

(c) washing the reaction product to remove excess metal complex.

13. A composition as recited in Claim 12, wherein the final reaction product is heated under vacuum to a temperature from ambient to about 1000°C.

14. A composition as recited in Claim 13, wherein the temperature is about 300° to about 400°C.

15. A composition as recited in Claim 12, wherein M is selected from the group consisting of Cr, Mo, W,
5 Mn, Re, Fe, Ru, Os, Co, Rh, Ir, Ni, Pd, Pt, Cu, Ag and Au.

16. A composition as recited in Claim 15, wherein M is selected from the group consisting of Ni, Pd and Pt.

10 17. A composition as recited in Claim 12, wherein the complex is $[(C_2H_5)_3P]_4M$ and M is selected from the group consisting of Ni, Pd and Pt.

2/3

FIG. 2A





FIG. 2B




3/3

FIG. 3A



FIG. 3B



INTERNATIONAL SEARCH REPORT

Intern. Appl. No.

PCT/US 94/11043

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C01B31/00 C07F15/04 C07F15/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	NATURE, vol.362, no.6420, 8 April 1993, LONDON GB pages 522 - 525 P. M. AJAYAN ET AL. cited in the application see page 524 : right-hand column : end 1st paragraph ---	1,2,4,5
A	NATURE, vol.361, no.6410, 28 January 1993, LONDON GB pages 333 - 334 P. M. AJAYAN ET AL. cited in the application ---	

-/--

☒ Further documents are listed in the continuation of box C.

☐ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

27 December 1994

Date of mailing of the international search report

10. 01. 95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Brebion, J

INTERNATIONAL SEARCH REPORT

Intern. Appl. No.
PCT/US 94/11043

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, vol.116, no.17, 24 August 1994, WASHINGTON, DC US pages 7935 - 7936 J. M. PLANEIX ET AL. see the whole document	1, 2, 4
A	-----	6, 8, 10, 12, 13, 15